



# ▶ DPF 510 Vinyl Film

## Digital Print Pressure-Sensitive Vinyl Film

DPF 510 is a 100 micron monomeric film with a clear\*, solvent-based pressure-sensitive adhesive. The two-sided polycoated liner provides excellent lay-flat properties. The high-quality adhesive provides far superior adhesion and cohesion properties than water-based adhesive. DPF 510 is available in a white gloss finish. DPF 510 is rated for outdoor durability up to 3 years (unprinted). Printed durability is dependent on the ink system used.

### APPLICATIONS & FEATURES

- Short-term promotional and display graphics, including kiosks, POP displays and real estate signage.
- Excellent printability on Eco-Solvent, Solvent and Latex print systems.
- Ideal for interior and exterior applications on flat surfaces.

### PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
<b>SURFACE FINISH</b>	Gloss Meter 60° Reflection	70 to 90 Gloss Units (Gloss)	
<b>THICKNESS</b>	Micrometer, Federal Bench Type	100 micron	
<b>TENSILE STRENGTH</b>	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 15.0 lb/in	≥ 2.7 kg/cm
<b>ELONGATION</b>	Instron Tensile Tester as above	≥ 200%	
<b>SHELF LIFE (IN BOX)</b>	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	1 year from factory shipment	
<b>APPLICATION TEMPERATURE RANGE</b>	On clean, dry substrate	10°C to 32°C	
<b>SERVICE TEMPERATURE RANGE</b>	On clean, dry substrate	-29°C to 65°C	
<b>DIMENSIONAL STABILITY</b>	158°F (70°C), 48 hours, on aluminum panel	0.25 mm	
<b>PEEL ADHESION</b>	PSTC-1, 15 min, 70°F (21°C)	≥ 0.36 kg/cm	
<b>LINER RELEASE</b>	TLMI Release at 90°, 300 in/min (760 cm/min)	7.9 g/cm	





\* Gray tinted adhesive is available as a custom construction. Please contact your sales rep.  
 Matte finish is available as a custom construction. Please contact your sales rep.  
 Standard Terms & Conditions Apply








## TERMS & CONDITIONS

*The following is made in lieu of all warranties expressed or implied:*

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

September 2015

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA  
EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands  
UK:  P6 Parklands, Heywood Distribution Park, Heywood, Lancashire OL102TT, UK  
INDIA:  4F1 Court Chambers 35, New Marines Lines, Mumbai 400 020, India

 800 232 7161/+1 714 985 6300  800 329 2756  
 +31 70 354 4311  +31 70 355 7721  
 +44 161 884 0592  +31 70 355 7721  
 +91 99 6755 3895

arlon.com